


PERKEMBANGAN BATERAI

Prof. Dr. Eng. Agus Purwanto



SEJARAH BATERAI

- 1800 Voltaic pile: silver zinc
- 1836 Daniell cell: copper zinc
- 1859 Planté: rechargeable lead-acid cell
- 1868 Leclanché: carbon zinc wet cell
- 1888 Gassner: carbon zinc dry cell
- 1898 Commercial flashlight, D cell
- 1899 Junger: nickel cadmium cell



SEJARAH BATERAI

- 1946 Neumann: sealed NiCd
- 1960s Alkaline, rechargeable NiCd
- 1970s Lithium, sealed lead acid
- 1990 Nickel metal hydride (NiMH)
- 1991 Lithium ion
- 1992 Rechargeable alkaline
- 1999 Lithium ion polymer

NOMENKLATUR BATERAI



Duracell batteries

Two cells



9v battery

A real battery




6v dry cell

Another battery

More precisely





SEL ELEKTROKIMIA



Sel Elektrokimia

- Zinc is (much) more easily oxidized than Copper



- Maintain equilibrium electron densities
 - Add copper ions in solution to Half Cell II
- Salt bridge only carries negative ions
 - This is the limiting factor for current flow
 - Pick a low-resistance bridge



The Electrochemical Series

Most wants to reduce (gain electrons)

- Gold
- Mercury
- Silver
- Copper
- Lead
- Nickel
- Cadmium

But, there's a reason
it's a *sodium* drop

- Iron
- Zinc
- Aluminum^o
- Magnesium
- Sodium ^o
- Potassium
- **Lithium**

Most wants to oxidize (lose electrons)

Karakteristik Baterai

- Size
 - Physical: button, AAA, AA, C, D, ...
 - Energy density (watts per kg or cm^3)
- Longevity
 - Capacity (Ah, for drain of C/10 at 20°C)
 - Number of recharge cycles
- Discharge characteristics (voltage drop)



Karakteristik Baterai

- Cost
- Behavioral factors
 - Temperature range (storage, operation)
 - Self discharge
 - Memory effect
- Environmental factors
 - Leakage, gassing, toxicity
 - Shock resistance



Primary (Disposable) Batteries

- Zinc carbon (flashlights, toys)
- Heavy duty zinc chloride (radios, recorders)
- Alkaline (all of the above)
- Lithium (photoflash)
- Silver, mercury oxide (hearing aid, watches)
- Zinc air



Standard Zinc Carbon Batteries

- Chemistry

 - Zinc (-), manganese dioxide (+)

 - Zinc, ammonium chloride aqueous electrolyte

- Features

 - + Inexpensive, widely available

 - Inefficient at high current drain

 - Poor discharge curve (sloping)

 - Poor performance at low temperatures



Heavy Duty Zinc Chloride Batteries

- Chemistry

 - Zinc (-), manganese dioxide (+)

 - Zinc chloride aqueous electrolyte

- Features (compared to zinc carbon)

 - + Better resistance to leakage

 - + Better at high current drain

 - + Better performance at low temperature



Standard Alkaline Batteries

- Chemistry

 - Zinc (-), manganese dioxide (+)

 - Potassium hydroxide aqueous electrolyte

- Features

 - + 50-100% more energy than carbon zinc

 - + Low self-discharge (10 year shelf life)

 - ± Good for low current (< 400mA), long-life use


 - Poor discharge curve




Alkaline-Manganese Batteries

(2)

EVEREADY ENERGIZER ALKALINE "D" SIZE



Alkaline Battery Discharge



Lithium Manganese Dioxide

- Chemistry

Lithium (-), manganese dioxide (+)

Alkali metal salt in organic solvent electrolyte

- Features

- + High energy density


- + Long shelf life (20 years at 70°C)

- + Capable of high rate discharge

- Expensive



Lithium v Alkaline Discharge



Secondary (Rechargeable) Batteries

- Nickel cadmium
- Nickel metal hydride
- Alkaline
- Lithium ion
- Lithium ion polymer
- Lead acid



Nickel Cadmium Batteries

- Chemistry

 - Cadmium (-), nickel hydroxide (+)

 - Potassium hydroxide aqueous electrolyte

- Features

 - + Rugged, long life, economical

 - + Good high discharge rate (for power tools)

 - Relatively low energy density

 - Toxic



NiCd Recharging

- Over 1000 cycles (if properly maintained)
- Fast, simple charge (even after long storage)

C/3 to 4C with temperature monitoring


- Self discharge

10% in first day, then 10%/mo


Trickle charge (C/16) will maintain charge

- Memory effect

Overcome by 60% discharges to 1.1V



NiCd Memory Effect



Nickel Metal Hydride Batteries

- Chemistry

LaNi₅, TiMn₂, ZrMn₂ (-), nickel hydroxide (+)

Potassium hydroxide aqueous electrolyte

- Features

- + Higher energy density (40%) than NiCd


- + Nontoxic

- Reduced life, discharge rate (0.2-0.5C)

- More expensive (20%) than NiCd



NiMH Battery Discharge



Voltage and capacity of DURACELL DR30 Ni-MH batteries at various discharge temperatures and rates.

[Conditions: Charge: 1C to $-\Delta V = 60\text{mV}$ @ 21°C (70°F)]


NiMH Recharging

- Less prone to memory than NiCd
- Shallow discharge better than deep
 - Degrades after 200-300 deep cycles
 - Need regular full discharge to avoid crystals
- Self discharge 1.5-2.0 more than NiCd
- Longer charge time than for NiCd



To avoid overheating



NiMH Memory Effect



NiCd v NiMH Self-Discharge




Secondary Alkaline Batteries

- Features

- 50 cycles at 50% discharge
- No memory effect
- Shallow discharge better than deeper



NiCd v Alkaline Discharge



Lead Acid Batteries

- Chemistry

 - Lead

 - Sulfuric acid electrolyte

- Features

 - + Least expensive

 - + Durable

 - Low energy density

 - Toxic



Lead Acid Recharging

- Low self-discharge
 - 40% in one year (three months for NiCd)
- No memory
- Cannot be stored when discharged
- Limited number of full discharges
- Danger of overheating during charging



Lead Acid Batteries

- Ratings

 - CCA: cold cranking amps (0F for 30 sec)

 - RC: reserve capacity (minutes at 10.5v, 25amp)

- Deep discharge batteries

 - Used in golf carts, solar power systems

 - 2-3x RC, 0.5-0.75 CCA of car batteries

 - Several hundred cycles



Lithium Ion Batteries

- Chemistry

 - Graphite (-), cobalt or manganese (+)

 - Nonaqueous electrolyte

- Features

 - + 40% more capacity than NiCd

 - + Flat discharge (like NiCd)

 - + Self-discharge 50% less than NiCd

 - Expensive



Lithium Ion Recharging

- 300 cycles
- 50% capacity at 500 cycles



Lithium Ion Polymer Batteries

- Chemistry

 - Graphite (-), cobalt or manganese (+)

 - Nonaqueous electrolyte

- Features

 - + Slim geometry, flexible shape, light weight

 - + Potentially lower cost (but currently expensive)

 - Lower energy density, fewer cycles than Li-ion



Battery Capacity

Type	Capacity (mAh)	Density (Wh/kg)
Alkaline AA	2850	124
Rechargeable	1600	80
NiCd AA	750	41
NiMH AA	1100	51
Lithium ion	1200	100
Lead acid	2000	30



Discharge Rates

Type	Voltage	Peak Drain	Optimal Drain
Alkaline	1.5	0.5C	< 0.2C
NiCd	1.25	20C	1C
Nickel metal	1.25	5C	< 0.5C
Lead acid	2	5C	0.2C
Lithium ion	3.6	2C	< 1C




Recharging

Type	Cycles (to 80%)	Charge time	Discharge per month	Cost per kWh
Alkaline	50 (50%)	3-10h	0.3%	\$95.00
NiCd	1500	1h	20%	\$7.50
NiMH	300-500	2-4h	30%	\$18.50
Li-ion	500-1000	2-4h	10%	\$24.00
Polymer	300-500	2-4h	10%	
Lead acid	200-2000	8-16h	5%	\$8.50



Example: IBM ThinkPad T21 Model 2647



- Source: IBM datasheet
- Relatively-constant discharge

Lithium-ion Batteries in Notebooks

- Lithium: greatest electrochemical potential, lightest weight of all metals
 - But, Lithium metal is explosive
 - So, use Lithium-{cobalt, manganese, nickel} dioxide
- Overcharging would convert lithium-x dioxide to metallic lithium, with risk of explosion



IBM ThinkPad Backup Battery

- Panasonic CR2032 coin-type lithium-magnesium dioxide primary battery
 - Application: CMOS memory backup
 - Constant discharge, ~ 0.1 mA
 - Weight: 3.1g
 - 220 mA-h capacity



IBM ThinkPad T21 Main Battery

- Lithium-ion secondary battery
- 3.6 A-h capacity at 10.8V
- Back-of-the-envelope calculations from workload shown earlier:
 - Maximum: 47 minutes
 - Average: 2 hours, 17 minutes
 - Sleep: 19 hours?



References

- Manufacturers

www.duracell.com/OEM

data.energizer.com

www.rayovac.com/busoem/oem

- Books

T. R. Crompton, *Battery Reference Book*, Newnes, 2000

D. Berndt, *Maintenance-Free Batteries*, Wiley, 1997

C. Vincent & B. Scrosati, *Modern Batteries*, Wiley, 1997

I. Buchmann, *Batteries in a Portable World*, www.buchmann.ca

